



Reliability Test Report

Product Name: CA-IS306X

Report Version: V1.1



Contents

1.	Overv	/iew	3
2.	Part N	lumber List	3
3.	Produ	ıct Information	3
	3.1.	Wafer Information	3
	3.2.	Package Information	3
4.	Reliab	oility Qualification Plan	4
	4.1.	Device Qualification Test Requirements	4
	4.2.	Nonhermetic Package Qualification Test Requirements	4
5.	Reliab	oility Test Results	5
	5.1.	Device Reliability Test Results	5
	5.2.	Package Reliability Test Results	5
6	Concl	usion	5



1. Overview

Reliability testing of microelectronic products is a risk mitigation process designed to ensure the service life of device in customer applications. Semiconductor wafer manufacturing process and package-level reliability can be assessed in a variety of ways and may include accelerated environmental test conditions. Chipanalog evaluates manufacturability of the device to verify a robust silicon and assembly flow to ensure continuity of supply to customers. Chipanalog qualifies new devices, significant changes, and product families based on JEDEC JESD47. CA-IS306X series chips are packaged with the same wafer. The differences between part numbers are the package and bonding diagram. The data shown is representative of the material sets, processes, and manufacturing sites used by the device family.

2. Part Number List

Package Type	Part Number
SOIC16-WB(W)	CA-IS3062W/CA-IS3062VW

Note: JEDEC specification is designed to also qualify a family of similar components utilizing the same fabrication process, design rules, and similar circuits. The family qualification may also be applied to a package family where the construction is the same and only the size and number of leads differs.

3. Product Information

3.1. Wafer Information

Wafer ID	SHENGFO_P	SHENGFO_S	SATURN
Die Tech	18BCD	18BCD	18BCD

3.2. Package Information

Assembly site	UNIMOS	JCET-D8
FT site	UNIMOS	JCET-D8
Package	SOIC16-WB(W)	SOIC16-WB(W)
Lead frame	Cu	Cu
Bond wire	25um Au	25um Au
MSL level	MSL3	MSL3



4. Reliability Qualification Plan

4.1. Device Qualification Test Requirements

Stress	Ref.	Abbv.	Conditions	Duration /Accept	
Electrical Parameter	JESD86	ED	Per Datasheet	Per Datasheet	
Assessment	723000		rei Datasileet		
High Temperature	JESD22-A108,	HTOL	T _J ≥ 125°C	1000 hrs/0 Fail	
Operating Life	JESD85	HIOL	Vcc ≥Vcc max	1000 HIS/O Fall	
Human Body Model	JS-001	ESD-	T _A = 25°C	Classification	
ESD	13-001	HBM	1A = 25 C	Classification	
Charged Device	15 003	ESD-	T _A = 25°C	Classification	
Model ESD	JS-002	CDM	1A = 25 C	Classification	
Latch-Up	JESD78	LU	Class I or Class II	0 Fail	

4.2. Nonhermetic Package Qualification Test Requirements

Stress	Ref.	Abbv.	Conditions	Duration /Accept
MSL Preconditioning	JESD22-A113	PC	Per appropriate MSL level per J-STD-020	Electrical Test (optional)
High Temperature Storage	JESD22-A103 & A113	HTSL	150°C, 1000 hrs	1000 hrs/0 Fail
Temperature Humidity Bias	JESD22-A101	ТНВ	85°C, 85% RH, V _{CC} max	1000 hrs/0 Fail
Highly Accelerated Temperature and Humidity Stress	JESD22-A110	HAST	130°C/110°C, 85% RH, 33.3/17.7 psia, V _{CC} max	96/264 hrs/0 Fail
Temperature Cycling	JESD22-A104	TC	-65°C to 150°C	500 cycles/0 Fail
Unbiased Temperature/Humidity	JESD22-A102	AC	121°C, 100% RH, 29.7psia	96 hrs/0 Fail
Unbiased Temperature/Humidity	JESD22-A118	UHAST	130°C/110°C, 85% RH, 33.3/17.7 psia	96/264 hrs/0 Fail
Bond Pull Strength	JESD22-B120	BPS	Characterization, Pre Encapsulation	Ppk≥1.66 or Cpk≥1.33
Bond Shear	JESD22-B116	BS	Characterization, Pre Encapsulation	Ppk≥1.66 or Cpk≥1.33
Solderability M2003 JESD22-B102 SD		Characterization	95% coverage	

Note: Either HAST or THB may be chosen.



5. Reliability Test Results

5.1. Device Reliability Test Results

Stress	Condition	Duration	Sample Size	Result	Classification
ED	Per Datasheet	/	10*3 lots	Pass	/
HTOL	$T_A = 125$ °C, $V_{CC} = 5.5$ V	1000 hrs	77*3 lots	Pass	/
ESD-HBM	T _A = 25°C	/	3*1 lot	Pass	Class 3A
ESD-CDM	T _A = 25°C	/	3*1 lot	Pass	Class C3
LU	T _A = 25°C	/	3*1 lot	Pass	Class I A

5.2. Package Reliability Test Results-UNIMOS

Package Type: SOIC16-WB					
Stress	Condition	Duration	Sample size	Results	
PC	MSL 3	/	231*3 lot	Pass	
HTSL	T _A = 150°C	1000 hrs	77*3 lot	Pass	
HAST	130°C, 85% RH, 33.3psia, Vcc=5.5V	96 hrs	77*3 lot	Pass	
TC	-65°C to 150°C	500 cycles	77*3 lot	Pass	
UHAST	130°C, 85% RH, 33.3psia	96 hrs	77*3 lot	Pass	
BPS	JESD22-B120	/	30 bonds/5 ea.	Pass	
BS	JESD22-B116	/	30 bonds/5 ea.	Pass	
SD	Steam aging, 245°C dipping	5s	22 leads*3 lot	Pass	

Note: 1 lot package reliability test data comes from qualification of CA-IS3062W, another 2 lot package reliability data refers to generic data of same package family.

5.3. Package Reliability Test Results-JCET

	Package Type: SOIC16-WB					
Stress	Condition	Duration	Sample size	Results		
PC	MSL 3	/	231*3 lot	Pass		
HTSL	T _A = 150°C	1000 hrs	77*3 lot	Pass		
HAST	130°C, 85% RH, 33.3psia, Vcc=5.5V	96 hrs	77*3 lot	Pass		
TC	-65°C to 150°C	500 cycles	77*3 lot	Pass		
UHAST	130°C, 85% RH, 33.3psia	96 hrs	77*3 lot	Pass		
BPS	JESD22-B120	/	30 bonds/5 ea.	Pass		
BS	JESD22-B116	/	30 bonds/5 ea.	Pass		
SD	Steam aging, 245°C dipping	5s	22 leads*3 lot	Pass		

Note: package reliability data refers to generic data of same package family.



6. Conclusion

CA-IS306X series products are qualified with JEDEC standards.



Disclaimer

This information is provided to assist customers in design and development. It could change for technology innovation without notice.

The devices are shipped after passing final test. Customers are responsible to conduct sufficient engineering and additional qualification testing to determine whether a device is suitable for use in their applications.

License to customers to use the information is limited to the development of applications using the device. Apart from above, the information shall not be reproduced or displayed, and Chipanalog shall not be liable for any claims, compensation, costs, losses or liabilities arising out of the use of the information.

Trademarks

Chipanalog Inc. ® 、Chipanalog ® are trademarks of Chipanalog.

Revision History

Revision	Change Log	Date
V1.0	Initial release	Aug, 2022
V1.1	Add JCET package reliability result	2024.11.25